

| Introduction

Alkaseal is used as film-forming non-yellowing protective sealer for concrete floors.

In construction, acrylic sealers are commonly employed as adhesives for bonding materials such as concrete, metal, and wood. They enhance structural integrity, improve load-bearing capacity, and provide resistance to environmental factors like moisture, chemicals, and temperature fluctuations. Acrylic sealers are also utilized in flooring systems, where they create durable surfaces ideal for industrial and commercial settings.

| Where it could be used.

As a primer, acrylic sealer and bonding agent on concrete and mortar stone, Cement renderings, asbestos cement, timber, sub-fill for coving, as a bonding agent for: floor toppings, mortar screeds and even for impregnating and selling cement-based floorings in warehouses and stores, warehouses and stores, garages, boiler rooms and corridors.

| Benefits

- Suitable for use on dry and damp substrates,
- Low viscosity, Excellent penetration and adhesion,
- Excellent bond strength,
- Easy application/Can be applied by brush or roller,
- Multi-purpose use,
- Protects new concrete from abuse,
- Rejuvenates worn surfaces, to a smooth finish,
- Designed to take heavy loads,
- Available in bulk quantities,
- Good mechanical resistance,
- Good chemical resistance,
- Short waiting times before subsequent coatings.

| How to Apply

Surface Preparation

- **Clean the Floor:** Thoroughly clean the floor to remove dirt, grease, oil, or any other contaminants. Use a degreaser or detergent for areas with oil or grease stains.
- **Repair Cracks and Holes:** Use a concrete patching material to fill in any cracks, holes, or imperfections. Allow it to fully dry before proceeding.
- **Grind or shot blast the Floor:** If the floor is smooth, you'll need to roughen it using a floor grinder or shot blaster. This helps the epoxy bond better to the concrete. Clean the dust afterward with a vacuum or broom.
- **Test for Moisture:** Check for moisture levels in the concrete by taping plastic sheets to the floor for 24 hours. If moisture builds up underneath, the floor may not be suitable for epoxy application.

Pre-mix with an electric stirrer for at least 3 minutes. Alkaseal is a versatile product and can be applied by brush, roller or spray. The recommended coating thickness is approximately 30-45 microns per coat.

After application and for the cleaning process, Xylene can be used for cleaning tools and equipment before the mixed compound begins to harden. Once cured, it must be removed mechanically.

| Important Notes

- Do not add any water.
- Do not apply Alka Seal on any substrates where significant vapor pressure may occur.
- Always ensure good ventilation when using Alka Seal in a confined space.
- Freshly applied Alka Seal should be protected from damp, condensation and water for at least 24 hours.
- If in doubt about the use or application of this product, or further information please contact our Alka Technical Department.
- Avoid contact with skin and eyes.
- Wear protective gloves and eye protection during work.
- If skin contact occurs, wash skin thoroughly.
- If in eyes, hold eyes open, flood with warm water and seek medical attention without delay.
- Avoid contact with foodstuffs and utensils.

A full Material Safety Data Sheet is available from Alka on request.

Technical and Physical Data

Form	Component A	transparent, liquid
	Transparent when applied.	
Density (at 20°C)	0.90 ± 0.05 kg/litre	
Application Temperature(ambient & substrate)	Minimum substrate temperature: +8°C Maximum substrate temperature: + 30°C Maximum relative humidity: ~ 80%	
Cure times	Touch Dry:	8 Hours @ 20°C approx.
	Light traffic:	3 Days @ 20°C approx.
	Full cure:	7 days @ 20°C approx.
Substrate MoistureContent	Maximum of 12% by weight or ≤ 80% relative humidity.	
Storage	Minimum of 12 months in unopened containers when stored free from frost in dry conditions between 10°C and 50°C. Component B is classed as non- hazardous for transportation.	
Packaging	Pre-proportioned unit 20 Litres.	

All products are subject to Alka terms and conditions. Read the full version on our website prior to any purchase.

| Contact us

ALKA COATINGS / ABN: 70 652 323 487

24/7 Toll-Free Emergency Response line for SDS: 1800 921 288

87 Market St, Smithfield 2164, New South Wales, Australia.

Phone: 1300 51 51 50 / www.alka.au

info@alka.au / Find us on social media.